



FLORPRIME WB

WATER BASED EPOXY PRIMER

PRODUCT DESCRIPTION

FLORPRIME WB is a solvent free clear two-pack low viscosity epoxy resin primer. It is used for cementitious substrates prior to application of epoxy or polyurethane

PRODUCT ADVANTAGES

- Being water based excellent wetting of cementitious surface.
- Gives very good adhesion to the top coat.
- Solvent free
- Can be applied on Concrete, Metal, Wood etc.

PHYSICAL CHARACTERISTICS

Application.....	Brush, Roller
Mixing ratio.....	1part Base to 4 parts Hardener by weight
Pot Life.....	30 Minutes at 23°C
Drying Time.....	2 Hrs at 25 Deg Cent.
Coverage.....	Approximately 4-6 sq.mts /Kg /coat depending on substrate porosity, texture, temperature of substrate
Recommended No. of Coats.....	1

METHOD OF APPLICATION

APURVA's system should be installed by approved contractors. Following information should be used as a guideline.

1. SURFACE PREPARATION.

The long-term durability of the applied **FLORPRIME WB** is dependent on the adhesive bond achieved between the flooring material and substrate. It is most important therefore, that substrate surfaces is correctly prepared prior to application.

- New concrete or cementitious substrates should have been placed atleast 28 days and have a moisture content of less than 5% before topping with **FLORPRIME WB**.
- Before application, the surface to be coated, should be free from loose particles, rust, oils, grease, or earlier coatings and should be thoroughly dry.
- After surface is dry, all repair work like sealing of joints, crack filling of cavities and crevices should be carried out.
- If the surface is Tremix or smooth surface then Shot Blasting is carried out to make the surface rough in order to enhance the bonding of the primer.

2. MIXING

Pack components are pre-weighed for optimum performance. Never split packs. Empty contents of component B into a mixing container and pre-mix to assure the suspension of solids. Add component A and continue to mix to a uniform consistency for 1-2 minutes. Mix with slow speed drill and helical spinner head for 2 minutes.

: 2 :

3. APPLICATION

FLORPRIME WB must be applied immediately after mixing the two components. **FLORPRIME WB** is applied with a paint brush or roller to produce a thin film.

PACKAGING

FLORPRIME WB is available in 5 Kg composite packs for easy handling. Each pack consists of
4 Kg of Curing Agent (Component A)
1 Kg of Base (Component B)

STORAGE & SHELF LIFE

Store all components of **FLORPRIME WB** unopened in shade. Avoid excessive heat. The shelf life is 1 year in original, unopened container.

HANDLING AND SAFETY

Keep the containers tightly sealed when not in use. Avoid skin contact and inhalation of fumes (if any). While spraying it is advised to wear a mask. If it comes in contact with the body, wash affected parts of plenty of water. In case of persistent irritation, contact a physician.

The manufacturer reserves the right to change the specifications. Apurva India Limited products are guaranteed against material manufacture and are sold subject to the company's Terms and Conditions of Sale. Whilst we endeavour to ensure that advice, specifications, recommendations and information given is correct, we can not have control over how our products are applied and will not accept liability, directly or indirectly, arising from application of our materials.

Apurva's wide range of quality products meets the tough requirements of the building industry. Constant interaction with clients, regular improvisation to meet growing needs and a strong commitment to provide products that perform has made Apurva a truly trusted name in the field.

For further details please contact :

APURVA INDIA LIMITED

(FORMERLY APURVA BUILD CARE TECHNOLOGIES P LIMITED)
New Udyog Mandir No.2, 2nd Floor, Office No.2,
7C, Pitambar Lane, Mahim(w), Mumbai 400 016
Tel.No. 91 22 24475051/52/53/54/55, Fax No. 91 22 24475056
E.Mail: info@apurvaindia.in Website: www.apurvaindia.in



